

## Premband Primer

Fast-drying primer for the preparation of surfaces

### Composition

Premband Primer is comprised of oxidised bitumen in aromatic hydrocarbon solvent.

### Uses

Premband Primer is used as surface preparation to maintain surface cleanliness prior to the application of Premband.

### Characteristics

Premband Primer is:

- fast drying,
- easy to apply, and
- improves cathodic disbondment resistance.

### Surface Preparation

Surfaces must be clean, dry and free from rust, scale and non-adherent coatings. Preferably, the area will be grit blasted or well wire brushed.

### Application

See *Instructions for Use* for additional details. Apply Premband Primer evenly over the surface using a brush.

Application temperatures: 0°C to +50°C.

### Cleaning solvent

Premband Primer may be cleaned with white spirit.

### Availability

Premband Primer is available in 5 L tins. Other sizes may be available on request.

### Storage conditions

Store in a cool and dry place in original packaging.

### Waste material

Please minimise or avoid waste wherever possible. Please do not discard waste material, including packaging, in the surrounding environment. Follow all relevant legislation for disposal.

### Typical Properties

Colour	Black
Specific Gravity	0.94
Solids Content	58% w/w
Flash Point (c.c)	>23°C minimum
Drying Time	10-15 minutes
Surface Coverage	7-8 m <sup>2</sup> /litre (@ DFT 70 – 80 µm)

Important: Premier Coatings Ltd. pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Premier Coatings Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. Q09303) and an Environmental Management System registered to BS EN ISO 14001 (BSI Certificate no. EMS 677780).

Page 1 of 1  
Revision date: 17/10/2022