

TECHNICAL DATA SHEET

LEADERS IN CORROSION PREVENTION & SEALING TECHNOLOGY



Premseal Primer

Fast-drying primer for the preparation of surfaces

Composition

Premseal Primer is comprised of a bitumen solution.

Uses

Premseal Primer is used in conjugation with Premseal Waterproof Membrane in order to consolidate the substrate and ensure complete bond development.

Characteristics

Premseal Primer:

- is easy to apply,
- enhances tape adhesion, and
- enhances corrosion protection of the system.

Surface Preparation

Surfaces must be clean, dry and free from rust, scale and non-adherent coatings. Preferably, the area will be abrasive blast cleaned or well wire brushed.

Application

See *Instructions for Use* for additional detail. Apply Premseal Primer evenly over the surface using a brush.

Availability

Premseal Primer is available in 5 L, 25 L and 200 L drums.

Storage conditions

Store all components upright in original packaging in a cool and dry place. Keep away from heat, sparks and open flames.

Waste material

Please avoid or minimise waste wherever possible. Please do not discard waste material, including packaging, in the surrounding environment. Follow all relevant legislation for disposal.

Typical Properties

Specific Gravity	0.92
Solids Content	48% w/w
Flash Point	>39°C
Viscosity	500 cP
Surface Coverage	6-8 m ² /Litre
WFT	90-110 microns
DFT	45-60 microns

Important: Premier Coatings Ltd. pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Premier Coatings Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. Q09303) and an Environmental Management System registered to BS EN ISO 14001 (BSI Certificate no. EMS 677780).

Page 1 of 1 Revision date: 13/10/2022

