

# TECHNICAL DATA SHEET

LEADERS IN CORROSION PREVENTION & SEALING TECHNOLOGY



# Premstrip

Pre-formed bitumen sealing strip

#### Composition

Premstrip is a neutral compound based upon plasticised, high-melting point bitumen with inert siliceous fillers.

#### Uses

Premstrip is used to seal joints in pre-cast concrete units such as manhole rings, box culverts, tunnel and shaft segments, ogee pipes, etc.

Service temperature: -15°C to +40°C

#### **Characteristics**

Premstrip is:

- flexible.
- resistant to acids, alkali and salts,
- resistant to root penetration,
- resistant to microbial attack, and
- shows excellent adhesion to concrete.

#### **Application**

See Instructions for Use for additional detail.

Recommended Primer: Premstrip primer

Application temperature: -5°C to +40°C.

#### Availability

Premstrip is available in reels. A wide selection of sizes is available to suit various joint designs.

### Storage conditions

Store in a cool dry place in original packaging.

#### Waste material

Please avoid or minimise waste wherever possible. Please do not discard waste material, including packaging, in the surrounding environment. Follow all relevant legislation for disposal.

## **Typical Properties**

Colour	Black
Non-volatile content	100%
Specific gravity	1.37
Specific volume	730 cm <sup>3</sup> /kg
Softening point	>100°C
Extensibility	600%

Important: Premier Coatings Ltd. pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Premier Coatings Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. Q09303) and an Environmental Management System registered to BS EN ISO 14001 (BSI Certificate no. EMS 677780).

> Page 1 of 1 Revision date: 14/10/2022

