

VISCOTAQTM

PVC OUTERWRAP

All-Purpose Protective Tape

Description

Viscotaq PVC Outerwrap is a plasticized polyvinyl chloride sheeting coated on one side with a rubber resin, pressure sensitive adhesive. Available in black rolls.

Uses

A protective outerwrap tape for Premier Tapes and Viscotaq Coating Systems for above and below ground applications.

Features

- Easy to apply
- Good conformability
- Good impact resistance
- Cold applied
- UV Resistant

Surface Prep

The Viscotaq PVC Outerwrap shall be spirally wrapped using a minimum 1" (25 mm) overlap on all applications. Apply sufficient tension to provide continuous adhesion of the tape.

When applied over Viscotaq products, Viscotaq PVC Outerwrap should be wrapped with tension and a minimum of 50% overlap. The first and termination wraps should be a straight circumferential wrap. A ¼" (6.4 mm) section of Viscotaq product should still be visible at each end of the Viscotaq PVC Outerwrap application.



Viscotag PVC Outerwrap

TECHNICAL DATA

PROPERTIES	10 MIL (0.25 MM)		20 MIL (0.50 MM)	
	ENGLISH	METRIC	ENGLISH	METRIC
	Thickness (ISO 4593:1993E)	10 mils	0.25 mm	20 mils
Weight	0.07 lbs/ft ²	0.34 kg/m ²	0.14 lbs/ft ²	0.68 kg/m ²
Breaking Strength (ASTM 1000)	25 lbf/in.	225 N/50 mm	40 lbf/in.	360 N/50 mm
Elongation @ Break	200% min.	200% min.	150% min.	150% min.
Temperature Range	-22 to 175°F	-30 to 80°C	-22 to 175°F	-30 to 80°C
Breakdown Voltage	10 kV	10 kV	16 kV	16 kV
Roll Widths	2", 4", 6"	50, 100, 150 mm	2", 4", 6"	50, 100, 150 mm
Roll Length	100 ft	30 m	100 ft	30 m

Packaging

Tape Width	Rolls*/ Case	Coverage with 1" (25 mm) Overlap	Coverage with 50% Overlap
in.	ea.	ea.	ea.
2" (50 mm)	24	200 ft ² /case (18.58 m ² /case)	200 ft ² /case (18.58 m ² /case)
4" (100 mm)	12	300 ft ² /case (27.87 m ² /case)	200 ft ² /case (18.58 m ² /case)
6" (150 mm)	8	333 ft ² /case (30.94 m ² /case)	200 ft ² /case (18.58 m ² /case)

*All rolls are 100 feet (30 m) in length.

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.

Page 2 of 2

Revision date. 30.06.2022



Q. 09303 EMS 67780

PREMIER COATINGS LTD

TEL: +44 (0) 1233 770 663

EMAIL: enquiries@premiercoatings.com

WEB: www.premiercoatings.com

Headcorn Road, Smarden

Ashford, Kent TN27 8PJ

UNITED KINGDOM

